

HARDOX[®] 600

Data sheet

ABRASION RESISTANT PLATE

HARDOX 600 is an abrasion resistant plate with a hardness of 600 HBW, intended for applications requiring an extremely high abrasion resistance.

Applications

Liners, cutters, feeders, chutes, shredders, hammers, knives etc.

Chemical Composition

(ladle analysis)

Plate thickness mm	C	Si	Mn	P	S	Cr	Ni	Mo	B	CEV typv.	CET typv.
8– 30	0,45	0,7	1,00	0,015	0,010	1,2	2,5	0,8	0,004	0,73	0,55
(30)– 50	0,47	0,7	1,00	0,015	0,010	1,2	2,5	0,8	0,004	0,84	0,59

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

The steel is grain refined.

Hardness

HBW
570-640

Impact Properties

Typical value for
20 mm plate thickness

Test temperature °C	Impact energy Charpy-V, longitudinal J
-40 (-40 F)	20

Testing

Brinell hardness, HBW according to EN ISO 6506-1, on a milled surface 0,5–2 mm below plate surface per heat and 40 tons. Tests are made for every variation of 15 mm in the thickness of plates from the same heat.

Delivery Conditions

Q.

Dimensions

HARDOX 600 is supplied in plate thicknesses of 8-50 mm. More detailed information on dimensions is provided in our brochure 042-UK General Product Information WELDOX, HARDOX and ARMOX.

Tolerances

Thickness tolerances according to SSAB Oxelösund thickness precision guarantee AccuRollTech™.
- AccuRollTech™ meets the requirements of EN 10 029 Class A, but offers more narrow tolerances.
More detailed information is given in our brochure 042-UK General Product Information WELDOX, HARDOX and ARMOX.

According to EN 10 029.

- Tolerances on shape, length and width.
- Tolerances on flatness according to Class N (Normal tolerances).

HARDOX 600

Data sheet

Surface Properties

According to EN 10 163-2
 - Requirements according to Class A.
 - Repair welding is not allowed.

General Technical Delivery Requirement

According to our brochure 042-UK General Product Information WELDOX, HARDOX and ARMOX.

Heat Treatment and Fabrication

HARDOX 600 has obtained its mechanical properties by quenching and when necessary by means of subsequent tempering. The properties of the delivery condition can not be retained after exposure to service or preheating temperatures in excess of 250° (480°F). HARDOX 600 is not intended for further heat treatment.

For information concerning welding and fabrication, see our brochures on www.hardox.com or consult our Technical Customer Service.

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product. Grinding, especially of primer coated plates, may produce dust with high particle concentration. Our Technical Customer Service Department will provide further information on request.